



硬质胶合剂

南亚硬质胶合剂是PVC专用的接着材料，其胶合作用非一般之糊粘作用，而是和铜铁等金属焊接一样的作用(即分子间之接合)，因此，胶着效果极为良好，又使用时接合物不须加热，适于无热源地区或任何气候下之施工。

NAN YA'S VINYL ADHESIVE is a special material for PVC products. It is not a common glue, but serves same purpose as metal's electric welding (combining on element). Therefore, it cherishes the highest gluing efficiency.

It is unnecessary to conduct the combination by heater, and suitable for processing in any climate or any area without heat source.



胶合剂使用注意事项

1. 涂抹胶合剂之前，务必要使管道之胶着面清洁，干净，若胶着面不洁，如油污、潮湿、灰尘等存在，均会使接着力减低。
2. 胶合剂涂抹时务必要均匀，尤其是雌、雄两管管端更是如此，另外，气温较高时，胶合剂涂抹及插接应迅速以避免未插时胶合剂就已干固，气温较低时，胶合剂涂抹后，待部分溶剂挥发，粘度增加时始予插接。
3. 胶粘剂固化过程中(至少2小时)不可晃动胶粘处，胶粘后，至少应等待24小时，始可进行通水(试压另依国家规范)。
4. 涂抹胶合剂并套接后，在套接处如有溢出(挤出)之胶合剂，务必擦拭干净，反之该处可能受过量胶合剂浸泡而软化并失去原有的承压强度。
5. 瓶盖开启使用后，若呈现流动性不良，请勿使用。

注：本资料中的数据若有更改，恕不另行通知。

*胶合剂符合轻工业标准QB/T 2568-2002(2009)标准

*禁止食用

*包装类别：180KG, 1000G, 700G, 350G, 80G

*已获得台湾绿建材标章证书，字号GBM0100585